

ISO/IEC 17025 Certified Third Party Test Report

DATE ISSUED: February 25, 2019 FILE: TABLEC.A021919A
DATE REVISED: April 5, 2019
CLIENT: A-1 Tablecloth Company ATTN: James Onello
450 Huyler Street, Ste 102
South Hackensack, NJ 07606

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Name: Majestic
Style: 120" Wide
Ref: One Color of 40 Tested
Color White

TEST PROCEDURE:

TEST RESULTS:

NATIONAL FIRE PROTECTION ASSOCIATION 701-2010 TEST 1

	<u>AFTER-FLAME</u>	<u>DRIP BURN</u>	<u>WEIGHT LOSS</u>		
	*****	*****	*****		
LENGTH:	0.00 Seconds	0.00 Seconds	23.75%		
LENGTH:	0.00 Seconds	0.00 Seconds	14.06%		
LENGTH:	0.00 Seconds	0.00 Seconds	18.54%		
LENGTH:	0.00 Seconds	0.00 Seconds	11.49%		
LENGTH:	0.00 Seconds	0.00 Seconds	21.51%	Std Dev:	4.03%
LENGTH:	0.00 Seconds	1.37 Seconds	18.86%	3 Std Dev:	12.08%
LENGTH:	0.00 Seconds	0.00 Seconds	17.05%		
LENGTH:	0.00 Seconds	0.88 Seconds	21.35%	3 Std Dev + Mean:	31.25%
LENGTH:	0.00 Seconds	0.00 Seconds	23.43%		
LENGTH:	<u>0.00 Seconds</u>	<u>0.00 Seconds</u>	<u>21.70%</u>		
	0.00 Seconds	0.23 Seconds	19.17%		

TEST RESULT: Pass

6-1 CALCULATION OF PERCENT WEIGHT LOSS:

6-1.1 The percent weight loss of each specimen shall be determined by the following equation:

$$\frac{(\text{Weight before test} - \text{Weight after test})}{(\text{Weight before test})} \times 100 = \text{Percent weight loss}$$

The percent weight loss shall be recorded.

6-1.2 The mean percent weight loss and the standard deviation for the sample consisting of 10 specimens shall be calculated.

6-1.3 Where the percent weight loss of any individual specimen exceeds the mean value plus three standard deviations, the test shall be repeated on another sample of 10 specimens. The mean percent weight loss and standard deviation for the second set of 10 specimens shall be calculated.




ISO/IEC 17025 Certified Third Party Test Report

FILE: TABLEC.A021919A
SAMPLE IDENTIFIED BY CLIENT AS:
Fabric Submitted
Name: Majestic
Style: 120" Wide
Ref: One Color of 40 Tested
Color White

7-1 PERFORMANCE CRITERIA:


- 7-1.1 Where fragments or residues of specimens that fall to the floor of the test chamber continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens, the material shall be recorded as failing test 1.
- 7-1.2 Where the average weight loss of the 10 specimens in a sample is greater than 40 percent, the material shall be recorded as failing the test.
- 7-1.3 Where the percent weight loss of any individual specimen in the second set of specimens exceeds the mean value of the second set plus three standard deviations calculated for the second set, the material shall be recorded as failing this test.
- 7-1.4 Where the specimens do not demonstrate performance in accordance with any of the conditions indicated in 7-1.1 through 7-1.3, the material shall be recorded as passing this test and shall be designated as flame resistant.

Signed For The Company By


Joseph Lin
Laboratory Manager

JG/02...JG/04




Stacy Sadowy
Quality Assurance Manager

Page 2 of 2